

Lehigh Testing Laborate

308 WEST BASIN ROAD . P.O. BOX 903 . NEW CASTLE, DE 19720 (302) 328-0500 • FAX (302) 328-0417



TEST REPORT

NATIONAL TRANSPORTATION SAFETY BOARD

ATTENTION: FRANK ZAKAR

490 L'ENFANT PLAZA EAST

WASHINGTON, DC 20594

DATE:

September 19, 2014

PO NO:

VERBAL

LEHIGH NO: R-34-30

PAGE:

1 of 1

MATERIAL:

GRAY CAST IRON

SAMPLE DESIGNATION: (1) SAMPLE: APPROX. 6" X 6" X 5/8" THICK SECTION

FROM 13.5" OD PIPE

CHEMICAL ANALYSIS (%)

Carbon	3.32
Sulfur	0.073
Silicon	1.68
Manganese	0.40
Phosphorus	1.46
Chromium	0.01
Nickel	0.02
Copper	0.08
Molybdenum	< 0.01
Vanadium	0.07
Boron	< 0.0006
Iron	Balance
Magnesium	0.02
Titanium	0.12
Cobalt	0.03
Arsenic	0.017

Results are for information only.

Procedure: QA-CH-P-048 Rev 1 (Leco C&S)

QA-CH-P-124 Rev 1 (ICP)

Lehigh Testing Laboratories, Inc.